

AD-A111 150

PRINCETON UNIV NJ DEPT OF CHEMICAL ENGINEERING

F/G 11/3

CHARACTERIZATION OF POLYMER-COATED OPTICAL FIBERS USING A TORSI--ETC(U)

JAN 82 J K GILLHAM, L T MANZIONE, U C PAEK

N00014-76-C-0200

UNCLASSIFIED

TR-23

NL

1 of 1

AD A
FILMED



END
DATE
FILMED
13-82
DTIC

AD A111150

(12)

LEVEL II

OFFICE OF NAVAL RESEARCH

Contract N00014-76-C-0200

Task No. NR 356-504

TECHNICAL REPORT NO. 23

CHARACTERIZATION OF POLYMER-COATED OPTICAL
FIBERS USING A TORSION PENDULUM

by

J. K. Gillham, L. T. Manzione, U. C. Paek and C. F. Tu

for publication in the
Journal of Applied Polymer Science

Princeton University
Polymer Materials Program
Department of Chemical Engineering
Princeton, NJ 08544

January 1982

Reproduction in whole or in part is permitted for
any purpose of the United States Government

This document has been approved for public release
and sale; its distribution is unlimited

Principal Investigator
J. K. Gillham
609/452-4694

DTIC
ELECTE
11115022
B

DTIC FILE COPY

820 118
431

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report #23	2. GOVT ACCESSION NO. AD A111150	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Characterization of Polymer-Coated Optical Fibers Using a Torsion Pendulum		5. TYPE OF REPORT & PERIOD COVERED Jan. 1980-Jan. 1982
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) J. K. Gillham, L. T. Manzione, U. C. Paek and C. F. Tu		8. CONTRACT OR GRANT NUMBER(s) N00014-76-C-0200
9. PERFORMING ORGANIZATION NAME AND ADDRESS Polymer Materials Program Department of Chemical Engineering Princeton University, Princeton, NJ 08544		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Task No. NR 356-504
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research 800 North Quincy St. Arlington, VA 22217		12. REPORT DATE JANUARY 1982
		13. NUMBER OF PAGES 15
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report)
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; Distribution Unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Torsion Pendulum Transitions Optical Fiber Modulus of Coatings Cure		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A freely oscillating torsion pendulum has been used to characterize the dynamic mechanical behavior of single polymer-coated optical fibers. The dynamical mechanical spectra of the polymer coatings exhibit a glass transition temperature (T_g), a cryogenic glassy-state relaxation (T_{sec}), and another cryogenic relaxation that is attributed to water present in the coating (T_{H_2O}). The shear modulus (G') of the coating was computed from the shear moduli of the composite specimen and the core, assuming that the coating and core deform through the same angle of oscillation.		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-LF-014-6601

CHARACTERIZATION OF POLYMER-COATED OPTICAL FIBERS
USING A TORSION PENDULUM

J. K. GILLHAM, Polymer Materials Program, Department of Chemical Engineering, Princeton University, Princeton, NJ 08544, L. T. MANZIONE, Bell Laboratories, Murray Hill, NJ 07974, U. C. PAEK, Western Electric Company, Engineering Research Center, Princeton, NJ 08540 and C. F. TU, Bell Laboratories, Atlanta, Georgia 30071.

SYNOPSIS

A freely oscillating torsion pendulum has been used to characterize the dynamic mechanical behavior of single polymer-coated optical fibers. The dynamical mechanical spectra of the polymer coatings exhibit a glass transition temperature (T_g), a cryogenic glassy-state relaxation (T_{sec}), and another cryogenic relaxation that is attributed to water present in the coating (T_{H_2O}). The shear modulus (G') of the coating was computed from the shear moduli of the composite specimens and the core, assuming that the coating and core deform through the same angle of oscillation. The glassy-state modulus was the same for both thin and thick coatings, although the intensity of the damping peaks, as measured by the logarithmic decrement, increased with coating thickness. Comparison of the dynamic mechanical behavior of a coated optical fiber and of a free film cast from the same reactive components shows that the polymer itself can absorb water at ambient conditions and display a mechanical relaxation at cryogenic temperatures. The T_{H_2O} and T_{sec} relaxations are coupled with respect to their intensities. Latent chemical reactivity was found in one coating above its maximum temperature of cure. In this, the temperature of cure determines the glass transition temperature.

✓
PER CALL
JC
By
Dist
Available
Dist
A

INTRODUCTION

Polymeric coatings on optical telecommunication fibers provide long-term protection from abrasion and environment which preserves the pristine strength of the fibers.¹ Mechanical properties of the coating are also important because they influence optical attenuation through microbending loss.² To protect the fiber from immediate environmental damage and to prevent beading of the fluid resin, the coating is formed immediately after the silica has been drawn from a preform rod. The coating is applied by pulling the fiber through a reservoir of reactive prepolymer fitted with a flexible rubber die.³ Hydrodynamic forces at the tip of the die center the fiber. The formulations used to produce the coatings studied in this report are UV-curable epoxy diacrylates.

Single optical fibers were employed as the specimens in conventional torsion pendulum experiments in which freely decaying waves were intermittently initiated. The sensitivity of a freely decaying torsion pendulum equipped with a nondrag optical transducer permits examination of the dynamic mechanical properties of coated and bare single filaments. The simple concentric geometry of the fiber and coating in a commercial optical fiber allows calculation of the actual in-phase shear modulus of the polymer coating from the composite properties, assuming that the coating is well bonded to the core and that the angular deformation of fiber and coating are the same.^{4,5} In situ characterization of optical fiber coatings is attractive because it is difficult to reproduce the exact radiation doses, curing conditions, and properties when preparing unsupported film specimens.

This report concerns the dynamic mechanical behavior of optical fiber coatings and the evaluation of the effects of elevated temperature and water

vapor on them using a torsion pendulum. A preliminary report has been published.⁵

EXPERIMENTAL

Specimens (5-6 cm) of coated fiber were cut from continuous lengths. They were examined closely to ensure that fiber and coating were concentric. Coatings were removed from some segments by soaking in tetrahydrofuran at room temperature for 12 h, and these were then used to obtain the shear modulus of the bare fiber. The diameters of the coated and bare fibers were measured to within ± 0.0001 cm with an optical microscope.

Dynamic mechanical spectra (ca. 1 Hz) were obtained using an automated torsion pendulum,⁶ a schematic diagram of which is shown in Figure 1. The specimen is mounted in clamps between the supporting and lower extender rods and lowered into the temperature-controlled chamber. The assembly is then coupled magnetically to the inertial disk; the latter remains permanently in the lower section of the instrument (see Fig. 2). The weight supported by the specimen is about 15 g. The polaroid disk serves as one part of the optical transducer. A beam of light passes through the oscillating disk and then through a second stationary polaroid sheet. The attenuated light is converted to an electrical analog signal by a linearly responding photodetector. The signal is monitored by an analog computer⁶ which computes the period of the oscillation and the damping coefficient for each wave. Recent publications^{7,8} report the use of digital computers for control and data processing of freely decaying torsion pendulum experiments.

The specimen is enclosed in a temperature- and humidity-controlled-and-measured environment of helium. Spectra were obtained between -190 and 115°C.

THEORY

The shear modulus of a rod of material can be defined as:

$$G' = \frac{\sigma}{\gamma} = \frac{\sigma}{r(d\theta/dl)} \quad (1)$$

For a long cylindrical shaft where $d\theta/dl$ is small and constant along the shaft, the shear stress is

$$\sigma = G'r \frac{d\theta}{dl} = \frac{G'r\theta}{L} \quad (2)$$

The torque per unit length is the summation of the moments of the shear forces:

$$T = \int_0^R \sigma r (2\pi r dr) = \frac{G'\theta}{L} \int_0^R 2\pi r^3 dr = \frac{G'\theta\pi R^4}{2L} \quad (3)$$

For a composite shaft with no slip at the interface, the torque can be expressed⁹ as (see Fig. 3)

$$\begin{aligned} T &= T_1 + T_2 \quad (\text{fiber} = 1, \text{coating} = 2) \\ &= \frac{G_1\theta_1}{L} \int_0^{R_1} 2\pi r^3 dr + \frac{G_2\theta_2}{L} \int_{R_1}^{R_2} 2\pi r^3 dr \end{aligned} \quad (4)$$

Assuming equiangular displacement in fiber and coating ($\theta_1 = \theta_2 = \theta$),

$$T = \frac{\theta\pi}{2L} [G_1 R_1^4 + G_2 (R_2^4 - R_1^4)] \quad (5)$$

This overall torque is related to an overall modulus of the composite (G') through eq. (3):

$$T = \frac{G'\theta\pi R}{2L} = \frac{\theta\pi}{2L} [G_1 R_1^4 + G_2 (R_2^4 - R_1^4)] \quad (6)$$

where G' of the composite is related to the period (P) of oscillation of the composite through¹⁰

$$G' = \frac{8\pi LI}{R^4 p^2} \quad (7)$$

The modulus of the coating can be determined from the period of oscillation of the composite and the shear modulus of the fiber through eqs. (6) and (7):

$$G'_2 = \frac{G'R_2^4 - G_1R_1^4}{R_2^4 - R_1^4} = \frac{(8\pi LI/P^2) - G_1R_1^4}{R_2^4 - R_1^4} \quad (8)$$

The loss modulus (G'') of a specimen is related to the logarithmic decrement (Δ) and the shear modulus (G') of the specimen by

$$G'' = \frac{G'\Delta}{\pi} \quad (9)$$

where

$$\Delta = \frac{1}{n} \ln \left(\frac{A_i}{A_{i+n}} \right)$$

in which n is the number of oscillations between the i th and $(i + n)$ th peaks of a decaying wave, and A_i and A_{i+n} are the peak amplitudes of the i th and $(i + n)$ th oscillations, respectively.

CALIBRATION

Calibration required the determination of the moment of inertia of the inertial mass of the torsion pendulum using a calibrated wire. An aluminum rod of measured geometry and mass was used as the inertial mass for calibrating a chromium-nickel alloy wire. The period of the oscillation was obtained by averaging over a number of oscillations using a stop watch; the procedure was repeated many times to decrease the statistical uncertainty.

The shear modulus of the calibration wire was determined to be 8.612×10^{11} dyn/cm² using eq. (7) and the geometry and mass of the rod and the period of oscillation. The calibrated wire was then used as the specimen in the torsion pendulum, and the moment of inertia of the system was determined to be 31.56 g-cm². The bare fiber was then used as the specimen, and its shear modulus (G_1') was determined: $G_1' = 1.936 \times 10^{11}$ dyn/cm². G_1' was taken to be independent of temperature over the temperature range in question (-190 to 115°C).

RESULTS AND DISCUSSION

Results were obtained for two specimens having coatings prepared in the same manner but having different thicknesses. The coating thickness ($R_2 - R_1$) was 0.0050 cm for the thin coating and 0.0115 cm for the thick coating. The specimens were conditioned in the apparatus in dry helium at 22°C for 16 h prior to obtaining thermomechanical data. Plots of the shear modulus of the coating (G_2') calculated from eq. (8) versus temperature for the thin and thick coatings are presented in Figure 4. Shear modulus data for the two specimens appear to be similar and within experimental error. Small differences are caused by the experimental error in measuring the radii due to the fourth-order dependence of G_2' on the radius.

The values for G_2' appear to be valid in the glassy region of the spectrum when the contribution of the polymer coating to overall specimen rigidity is equivalent to that of the hard core. The modulus of the silica fiber is almost an order of magnitude higher than that of the glassy coating, but the fourth-power dependence of the modulus on the radius [see eq. (7)] enhances the contribution of the coating to the overall rigidity.

The coating becomes rubbery above its glass transition temperature (T_g) where its real modulus is expected to drop by at least an order of magnitude. The contribution of the coating to the composite rigidity above T_g is therefore greatly reduced in comparison with the contribution of the core fiber. The sensitivity of the technique is therefore poor above the T_g of the coating. In principle, the problem can be avoided by forming the polymer on a core support of low modulus. The values of the glassy shear modulus shown in Figure 4 appear to be in good agreement with an earlier report of mechanical properties of a free film of UV-cured epoxy acrylate obtained with a mechanical spectrometer. At -100°C and 1 rad/sec, where G' is relatively independent of frequency, the report (11) shows $G' = 2.55 \times 10^{10}$ dyne/cm². This compares well with the value of 2.45×10^{10} dyn/cm² obtained by averaging the values obtained herein using the thin (2.60×10^{10} dyn/cm²) and thick (2.31×10^{10} dyn/cm²) specimens.

Figure 5 is a plot of the logarithmic decrement of the composite for both the thin and thick coatings. Two thermomechanical transitions were found in the spectra. A glass transition was found slightly above room temperature in each: 25°C for the thin coating and 34°C for the thick coating. A secondary relaxation (T_{sec}) associated with epoxy acrylate materials was found at -144°C in both coatings.

The intensity of the damping peaks increases with the amount of coating in the composite. The intensity of the damping peak at the glass transition temperature of the coating is plotted against the volume fraction and also against the volume of coating in Figure 6. The data plotted versus the volume of polymer coating provide a straight line that extrapolates to the low damping value of the glass fiber. It is accepted that the logarithmic decrement is

proportional to the volume fraction of dissipative material,¹² provided that the geometry is unchanged.

A free film of coating material was formed and used as a conventional torsion pendulum specimen after ASTM D-2236.¹³ The film was a rectangular solid with dimensions 0.063 cm x 0.254 cm x 5.40 cm. Figure 7 is a plot of the relative rigidity ($1/P^2$), which is directly proportional to the shear modulus,^{6,8} and logarithmic decrement versus temperature. The specimen had been conditioned 1 h in dry helium (ca. 50 parts per million H_2O) at 60°C, and its spectrum displayed a small but distinct damping peak between the more pronounced secondary (T_{sec}) and glass transition (T_g) damping peaks. The specimen was then further conditioned for 10 h at 60°C in dry helium, and the spectrum was again obtained (Fig. 8). The small damping peak was not present, indicating that it is associated with small amounts of water present in the polymer that are absorbed at ambient conditions. This relaxation, denoted T_{H_2O} ,¹⁴ was found to be completely reversible and controllable through the humidity of the conditioning atmosphere. This result on the free film indicates that water relaxations will generally be present under use conditions of optical fiber coatings of the epoxy acrylate type when used in the absence of a dry atmosphere.

A final example consists of the dynamic mechanical analysis of a fiber coated with a different epoxy acrylate formulation than that discussed earlier. The initial temperature scan (22 → -190 → 100°C) obtained after conditioning in dry helium at 22°C for 16 h is presented in Figure 9. The spectrum shows a secondary relaxation (T_{sec}), a water relaxation (T_{H_2O}), and a complex glass transition region. The subsequent scan from 100°C (100 → -190 → 115 → 30°C) showed no water relaxation, an increased intensity for the secondary relaxation (it has been reported¹⁴ that the T_{sec} and T_{H_2O} relaxations are coupled),

and a slightly elevated and somewhat narrower glass transition. This latter result indicates that this coating has latent reactivity at temperatures above its temperature of formation (which was essentially room temperature).

CONCLUSIONS

Dynamic mechanical properties of the polymeric coatings of optical fibers have been measured in situ using an automated torsion pendulum. The shear modulus of the coating was calculated from the moduli of the composite and core. The glassy modulus of one coating at -100°C was $2.45 \times 10^{10} \text{ dyn/cm}^2$, which is in good agreement with reports on unsupported film specimens.

Dynamic mechanical spectra of the coatings and free films were sensitive to water absorbed in the polymer which could be removed by extended periods of drying. A low-temperature water relaxation was coupled with a low-temperature relaxation of the dry polymer.

In one polymeric system, with the curing temperature ($\sim\text{RT}$) well below the maximum glass transition temperature, the material was incompletely cured. Heating above the temperature of formation increased T_g .

Partial support by the Chemistry Branch of the Office of Naval Research is acknowledged.

NOTATION

$1,2$	subscripts denoting fiber and coating, respectively
A_i	peak angular deformation corresponding to cycle number i
G'	in-phase shear modulus (dyn/cm^2)
G''	out-of-phase shear modulus (dyn/cm^2)
I	Moment of inertia (g-cm^2)
L	specimen length (cm)
l	spatial variable in axial direction
P	period (s)
R	radius (cm)
r	variable in radial direction
T	(torque (dyn-cm))
γ	shear strain
Δ	logarithmic decrement
σ	shear stress (dyn/cm^2)
θ	angular deformation

REFERENCES

1. H. Schonhorn, C. R. Kurkjian, R. E. Jeger, H. N. Vazirani, R. V. Albarino, and F. V. DiMarcello, *Appl. Phys. Lett.*, 29, 712 (1979).
2. D. Gloge, *Appl. Opt.*, 11(11), 2506 (1972).
3. L. L. Blyler, B. R. Eichenbaum, and H. Schonhorn, in *Optical Fiber Telecommunications*, S. E. Miller and A. G. Chynoweth, Eds., Academic, New York, 1979, p. 299.
4. L. T. Manzione, Ph.D. thesis, Department of Chemical Engineering, Princeton University, 1979.
5. J. K. Gillham, L. T. Manzione, C. F. Tu, and U. C. Paek, *Am. Chem. Soc., Organic Coatings Plast. Chem. Div. Prepr.*, 41, 357 (1979).
6. J. K. Gillham, *AIChE J.* 20(6), 1066 (1974); also *Polym. Eng. Sci.* 19(10), 676 (1979).

7. L. E. Stillwagon and L. T. Manzione, in Proceedings of North American Thermal Analysis Society, Boston, October 1980, pp. 89-94.
8. J. B. Enns, J. K. Gillham and M. J. Doyle, Am. Chem. Soc. Organic Coatings Plast. Chem. Div. Prepr., 43, 669 (1980); also, *ibid*, 45, 492 (1981).
9. J. C. Grawsie, Applied Mechanics for Engineers, Longmans, Green and Co., New York, 1967, p. 372.
10. L. E. Nielsen, Mechanical Properties of Polymers, Reinhold, New York, 1962.
11. C. R. Taylor, Bell Laboratories, Norcross, GA, unpublished results, March 1979.
12. N. G. McCrum, in Molecular Basis of Transitions and Relaxations, D. J. Meier, Ed., Gordon and Breach, London, 1978, p. 172.
13. ASTM Standards, Part 35, Plastics - General Test Methods, American Society of Testing and Materials, Philadelphia, PA, 1974.
14. J. K. Gillham, C. A. Glandt, and C. A. McPherson, in Chemistry and Properties of Crosslinked Polymers, S. Labana, Ed., Academic, New York, 1977, p. 491.

FIGURE CAPTIONS

- Fig. 1. Automated torsion pendulum.
- Fig. 2. Mounted specimen assembly ready for lowering into the vertical cavity of the temperature controlled enclosure.
- Fig. 3. Assumed geometry and deformation in a coated fiber under torsional loading.
- Fig. 4. Calculated in-phase shear modulus (G') of coating vs. temperature ($^{\circ}\text{C}$) for two specimens with different thicknesses of coatings: () thin coating, $R_1 = 0.0055$ cm, $R_2 = 0.0105$ cm, $L = 5.80$ cm; (o) thick coatings, $R_1 = 0.0055$ cm, $R_2 = 0.0170$ cm, $L = 5.70$ cm. Conditioning: $22^{\circ}\text{C}/16\text{h}/\text{dry}$ helium. Experiment: $22 \rightarrow -190 \rightarrow -100^{\circ}\text{C}$. $\Delta T/\Delta t = 1^{\circ}\text{C}/\text{min}$. Plot shown: $-190 \rightarrow 100^{\circ}\text{C}$.
- Fig. 5. Logarithmic decrement (Δ) of composite vs. temperature ($^{\circ}\text{C}$) for two specimens with different coating thicknesses (same specimens as for Fig. 4): (■) thin coating, $T_g = 25^{\circ}\text{C}$ (0.27 Hz), $T_{\text{sec}} = -144^{\circ}\text{C}$ (0.33 Hz); (o) thick coating $T_g = 34^{\circ}\text{C}$ (0.39 Hz), $T_{\text{sec}} = 144^{\circ}\text{C}$ (0.72 Hz).
- Fig. 6. Logarithmic decrement (Δ) of composite at T_g of polymer coating vs. volume fraction (Δ) and volume (■) of coating in the composite.
- Fig. 7. Free film: relative rigidity ($1/P^2$) and logarithmic decrement (Δ) vs. T ($^{\circ}\text{C}$). Conditioning: $60^{\circ}\text{C}/1\text{ h}/\text{dry}$ helium. Plot: $60 \rightarrow -190 \rightarrow 60^{\circ}\text{C}$; $\Delta T/\Delta t = 1^{\circ}\text{C}/\text{min}$. $T_g = 40^{\circ}\text{C}$ (0.52 Hz) (decreasing temperature), 41.5°C (0.43 Hz) (increasing temperature). $T_{\text{H}_2\text{O}} = -71^{\circ}\text{C}$ (2.53 Hz), $T_{\text{sec}} = -138^{\circ}\text{C}$ (2.85 Hz).

- Fig. 8. Free film: relative rigidity ($1/P^2$) and logarithmic decrement (Δ) vs. T ($^{\circ}\text{C}$) (same specimen as in Fig. 7). Conditioning: $60^{\circ}\text{C}/11$ h/dry helium (see also Fig. 7). Plot: $60 \rightarrow -190 \rightarrow 60^{\circ}\text{C}$; $\Delta T/\Delta t = 1^{\circ}\text{C}/\text{min}$. $T_g = 41^{\circ}\text{C}$ (0.41 Hz), $T_{\text{sec}} = 134^{\circ}\text{C}$ (2.80 Hz) (decreasing temperature).
- Fig. 9. Composite: relative rigidity ($1/P^2$) and logarithmic decrement (Δ) vs. T ($^{\circ}\text{C}$). Conditioning: $22^{\circ}\text{C}/16$ h/dry helium. Plot: $22 \rightarrow -190 \rightarrow 100 \rightarrow -190 \rightarrow 115 \rightarrow 30^{\circ}\text{C}$; $\Delta T/\Delta t = 1^{\circ}\text{C}/\text{min}$. $R_1 = 0.0055$ cm, $R_2 = 0.0155$ cm, $L = 5.95$ cm; $T_g = 95^{\circ}\text{C}$ to 103°C , $T_{\text{H}_2\text{O}} = -67^{\circ}\text{C}$ (0.052 Hz), $T_{\text{sec}} = -136^{\circ}\text{C}$ (0.56 Hz) to -130°C (0.55 Hz).





Fig. 1



* NOT REMOVED IN RAISING OR LOWERING SPECIMEN

Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9

SP472-3/A1

472:GAN:716:enj
78u472-608TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Office of Naval Research Attn: Code 472 800 North Quincy Street Arlington, Virginia 22217	2	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 1211 Research Triangle Park, N.C. 27709	1
ONR Western Regional Office Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Eastern Regional Office Attn: Dr. L. H. Peebles Building 114, Section D 666 Summer Street Boston, Massachusetts 02210	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Director, Naval Research Laboratory Attn: Code 6100 Washington, D.C. 20390	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
The Assistant Secretary of the Navy (RE&S) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1	Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto, Marine Sciences Division San Diego, California 91232	1
		Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1

SP472-3/A3

472:GAN:716:enj
78u472-608TECHNICAL REPORT DISTRIBUTION LIST, GENNo.
Copies

Mr. James Kelley
DTNSRDC Code 2803
Annapolis, Maryland 21402

1

Mr. A. M. Anzalone
Administrative Librarian
PLASTEC/ARRADCOM
Bldg 3401
Dover, New Jersey 07801

1

SP472-3/B5

472:GAN:716:enj
78u472-608TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. Stephen H. Carr Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Picatinny Arsenal Attn: A. M. Anzalone, Building 3401 SMUPA-FR-M-D Dover, New Jersey 07801	1
Dr. M. Broadhurst Bulk Properties Section National Bureau of Standards U.S. Department of Commerce Washington, D.C. 20234	2	Dr. J. K. Gillham Department of Chemistry Princeton University Princeton, New Jersey 08540	1
Professor G. Whitesides Department of Chemistry Massachusetts Institute of Technology Cambridge, Massachusetts 02139		Dr. E. Baer Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1
Dr. D. R. Uhlmann Department of Metallurgy and Material Science Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. K. D. Pae Department of Mechanics and Materials Science Rutgers University New Brunswick, New Jersey 08903	1
Naval Surface Weapons Center Attn: Dr. J. M. Augl, Dr. B. Hartman White Oak Silver Spring, Maryland 20910	1	NASA-Lewis Research Center Attn: Dr. T. T. Serofini, MS-49-1 21000 Brookpark Road Cleveland, Ohio 44135	1
Dr. G. Goodman Globe Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1	Dr. Charles H. Sherman Code TD 121 Naval Underwater Systems Center New London, Connecticut 06320	1
Professor Hatsuo Ishida Department of Macromolecular Science Case-Western Reserve University Cleveland, Ohio 44106	1	Dr. William Risen Department of Chemistry Brown University Providence, Rhode Island 02192	1
Dr. David Soong Department of Chemical Engineering University of California Berkeley, California 94720		Dr. Alan Gent Department of Physics University of Akron Akron, Ohio 44304	1
Dr. Curtis W. Frank Department of Chemical Engineering Stanford University Stanford, California 94305		Mr. Robert W. Jones Advanced Projects Manager Hughes Aircraft Company Mail Station D 132 Culver City, California 90230	1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. C. Giori IIT Research Institute 10 West 35 Street Chicago, Illinois 60616	1	Dr. J. A. Manson Materials Research Center Lehigh University Bethlehem, Pennsylvania 18015	1
Dr. R. S. Roe Department of Materials Science and Metallurgical Engineering University of Cincinnati Cincinnati, Ohio 45221	1	Dr. R. F. Helmreich Contract RD&E Dow Chemical Co. Midland, Michigan 48640	1
Dr. Robert E. Cohen Chemical Engineering Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. R. S. Porter Department of Polymer Science and Engineering University of Massachusetts Amherst, Massachusetts 01002	1
Dr. T. P. Conlon, Jr., Code 3622 Sandia Laboratories Sandia Corporation Albuquerque, New Mexico	1	Professor Garth Wilkes Department of Chemical Engineering Virginia Polytechnic Institute and State University Blacksburg, Virginia 24061	1
Dr. Martin Kaufmann, Head Materials Research Branch, Code 4542 Naval Weapons Center China Lake, California 93555	1	Dr. Kurt Baum Fluorochem Inc. 680 S. Ayon Avenue Azusa, California 91702	1
Professor S. Senturia Department of Electrical Engineering Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Professor C. S. Paik Sung Department of Materials Sciences and Engineering Room 8-109 Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1
Dr. T. J. Reinhart, Jr., Chief Composite and Fibrous Materials Branch Nonmetallic Materials Division Department of the Air Force Air Force Materials Laboratory (AFSC) Wright-Patterson AFB, Ohio 45433	1	Professor Brian Newman Department of Mechanics and Materials Science Rutgers, The State University Piscataway, New Jersey 08854	1
Dr. J. Lando Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1	Dr. John Lundberg School of Textile Engineering Georgia Institute of Technology Atlanta, Georgia 30332	1
Dr. J. White Chemical and Metallurgical Engineering University of Tennessee Knoxville, Tennessee 37916	1		

LMED
-8